



Lliça Packagin Slu
 Carretera Sabadell a
 Granollers Km 11,1
 08185 Lliça de Vall (Spain)

TEL :
 France +33 (0) 1 46 35 12 37
 (Cadex)
 Spain: +34 934 759 100
 (Careo Iberica)
 email: info@llissapackaging.com

Lliça Coat

Folding Box Board GC2

Carton couché GC2

Specification	unit	Tolerances	230	250	275	300	325	350	400	440
Caliper / Epaisseur	µm	± 5%	380	430	480	520	525	565	655	720
Stiffness/ Rigidity (Taber-ST)	mN.m	± 15%	5,5	7,2	9,6	12,1	11,6	13,8	22,0	29,0
Stiffness (Taber- SM)	mN.m	± 15%	12,3	16,3	22,0	27,7	33,2	39,1	51,3	61,2

Substance / Grammage	g/m2	± 3%	ISO
Bending stiffness / Rigidity	mN.m	± 15%	ISO
Brightness / Blancheur	%	± 2	Recto-Verso / Top-Back
COBB 1n	g/m2	± 20	Recto-Verso / Top-Back
Suitability for laser coding	%	100	Aptitude au marquage laser (data matrix)
Suitability for inkjet	%	100	Aptitude au jet d'encre (data matrix)
Robinson test	<1 scale from 0 to 4		

Test Condition:

Temperature 23± 1 C, Relative humidity 50% ± 2